



WE 25N (T25140)

DESCRIPTION

WE 25N is polyether foam with a homogeneous open cell structure.

WE 25N can be used in the furniture and upholstery market and bedding application market.

Can be used as top mattress, back cushions, paddings,

SPECIFICATIONS

Property	Unit	Method	Value
Net density	kg/m ³	ISO 845	21-23
Ild 40%	N	ISO 2439/B	140 (±15%)

TYPICAL VALUES

Property	Unit	Method	Value
Elongation at break	%	ISO 1798	150
Tensile Strength	kPa	ISO 1798	115
DSV: Height loss	%	ISO 3385	4
DSV: Hardness loss	%	ISO 3385	30

Testing conditions are available for consultation

SPECIFIC INFORMATION

Production plant: Åndalsnes NO

Colour: Light blue

Gross foaming width: 2040 (-0/+20mm)

Lead time: 1 week

Minimum quantity:

Gross height of standard blocks: 1020 (-0/+20mm)