

WE 25S (T25110)



DESCRIPTION

WE 25S is polyether foam with a homogeneous open cell structure.

WE 25S can be used in the furniture and upholstery market and bedding application market.

Can be used as top mattress, back cushions, paddings,

SPECIFICATIONS

| Property | Unit | Method | Value |
|-------------|-------------------|------------|------------|
| Net density | kg/m ³ | ISO 845 | 21-24 |
| Ild 40% | N | ISO 2439/B | 110 (±15%) |

TYPICAL VALUES

| Property | Unit | Method | Value |
|---------------------|------|----------|-------|
| Elongation at break | % | ISO 1798 | 190 |
| Tensile Strength | kPa | ISO 1798 | 150 |
| DSV: Height loss | % | ISO 3385 | 6 |
| DSV: Hardness loss | % | ISO 3385 | 32 |

Testing conditions are available for consultation

SPECIFIC INFORMATION

Production plant: Åndalsnes NO

Colour: White

Gross foaming width: 2040 (-0/+20mm)

Lead time: 1 week

Minimum quantity:

Gross height of standard blocks: 1010 (-0/+20mm)



