

WE 35XS (T35100)



DESCRIPTION

WE 35XS is polyether foam with a homogeneous open cell structure.

WE 35XS can be used in the furniture and upholstery market and bedding application market.

Can be used as mattresses, seat cushions,

SPECIFICATIONS

Property	Unit	Method	Value
Net density	kg/m ³	ISO 845	31-34
Ild 40%	N	ISO 2439/B	100 (±15%)

TYPICAL VALUES

Property	Unit	Method	Value
Elongation at break	%	ISO 1798	265
Tensile Strength	kPa	ISO 1798	145
DSV: Height loss	%	ISO 3385	2
DSV: Hardness loss	%	ISO 3385	20

Testing conditions are available for consultation

SPECIFIC INFORMATION

Production plant: Åndalsnes NO

Colour: White

Gross foaming width: 2050 (-0/+20mm)

Lead time: 1 week

Minimum quantity:

Gross height of standard blocks: 1040 (-0/+20mm)



